



Manufacturers of Custom Welding Lines for Resale  
[www.selectrode.com](http://www.selectrode.com)

# SELECTRODE

## 1190

5% Silicon Flux Coated  
 Arc/Torch Aluminum Alloy

### INTERNATIONAL CLASSIFICATIONS

AWS/ASME A 5.3 E 4043  
 DIN 1732: EL -Al Si5

EN 573-3: E AlSi5

### FEATURES & APPLICATIONS

For arc welding aluminums alloyed with copper, silicon, and magnesium. Also excellent for joining dissimilar grades of aluminum.

5% Silicon aluminum arc welding electrode with exclusive self lifting slag. Other aluminum grades such as Al 99, Al Mn, etc. are also available.

- Unique self lifting slag.
- The only aluminum electrode manufactured in a "Low Temperature" 5/64 (2.0mm) x 10" (250mm) size.
- Pure white long shelf life extruded flux coating outlasts conventional products in moisture resistance.
- Can be manufactured in a variety of custom colors.
- Available in hermetically sealed PURE ALUMINUM pull ring cans or vacuum packed foil bags for extended shelf life.
- Also available in TIG form as item code 6009, in MIG form as item code 7090 and as a bare torch brazing alloy as item code 2190.

### ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

**Flux Color:** White or Custom Colors

Si	Cu	Fe	Mg	Mn	Zn	Ti	Be	Al
5.25	.23	.8	.04	.04	.08	.20	.0008	Bal.

## TYPICAL MECHANICAL PROPERTIES

<b>Undiluted Weld Metal</b>	<b>Maximum Value Up to:</b>
Tensile Strength	32,000 psi (230 MPa)
Yield Strength	20,000 psi (150 MPa)
Elongation	18%

## WELDING CURRENT & INSTRUCTIONS

**Recommended Current:** DC Reverse (+)

Diameter (mm)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Minimum Amperage	20	50	70	110
Maximum Amperage	60	80	120	150

**Welding Techniques:** Start by using the upper portion of the amperage range. Feed the electrode quickly and move fast maintaining a very close arc gap.

**Welding Positions:** Flat, Horizontal

**Deposition Rates:**

Diameter (mm)	Length (mm)	Weldmetal/ Electrode	Electrodes per lb (kg) of Weldmetal	Arc Time of Deposition min/lb (kg)	Amperage Settings	Recovery Rate
5/64 (2.0)	10" (250)	.08oz (2.6g)	184 (404)	176 (337)	40	90%
3/32 (2.5)	14" (350)	.14oz (4.3g)	114 (251)	110 (242)	70	90%
1/8 (3.25)	14" (350)	.23oz (6.5g)	70 (153)	62 (136)	110	90%
5/32 (4.0)	14" (350)	.33oz (9.6g)	48 (107)	47 (103)	135	90%

## APPROXIMATE ELECTRODE PACKAGING & DIMENSIONS

Diameter (mm)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Length (mm)	10" (250)	14" (350)	14" (350)	14" (350)
Electrodes / lb	80	49	33	23
Electrodes / kg	176	108	73	51