



Manufacturers of Custom Welding Lines for Resale
www.selectrode.com

SELECTRODE
1152
310-16

INTERNATIONAL CLASSIFICATIONS

AWS/ASME A 5.4 E 310-16
DIN 8556: E 25.20 R 26
NFA 81-343: EZ 25.20 R 26

EN 1600: E 25.20 R 32
ISO 3581: E 25.20 R 26

FEATURES & APPLICATIONS

Ideal for joining unknown grades of stainless especially in high temperature applications
Smooth running electrode for joining type 310 stainless and especially for dissimilar combinations of steels

- High alloy content allows use in high temperature applications for scale resistance.
- Extra low spatter emission minimizes clean-up.
- Weld metal is non-magnetic.

ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

Microstructure: Fully austenitic with a ferrite number of 0.

Flux Color: Maroon

C	Mn	Si	S	P	Cr	Ni	Mo	Cu	Fe
.09	2.2	.4	.008	.018	26	21	.2	.1	bal

TYPICAL MECHANICAL PROPERTIES

Undiluted Weld Metal

Maximum Value Up to:

Tensile Strength	84,000 PSI (580 MPa)
Yield Strength	59,000 PSI (410 MPa)
Elongation	37%
Impact Energy	100J: 68oF (20°C), 60J: -320oF (-196°C)
Hardness	Brinell 200, Rockwell B88

WELDING CURRENT & INSTRUCTIONS

Recommended Current: DC Reverse (+) or AC

Diameter (mm)	1/16 (1.6)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Minimum Amperage	25	30	55	75	90
Maximum Amperage	35	50	75	110	140

Welding Techniques: Material to be welded should be clean of all contaminants. Maintain a short arc and use stringer beads rather than a weave technique.

Welding Positions: Flat, Horizontal, Vertical up, Overhead

Deposition Rates:

Diameter (mm)	Length (mm)	Weldmetal/ Electrode	Electrodes per lb (kg) of Weldmetal	Arc Time of Deposition min/ lb (kg)	Amperage Settings	Recovery Rate
1/16 (1.6)	10" (250)	.13oz (3.6g)	125 (275)	55 (121)	30	100%
5/64 (2.0)	12" (300)	.14oz (4g)	114 (251)	47 (103)	40	100%
3/32 (2.5)	12" (300)	.3 oz. (9g)	50 (109)	35 (76)	65	100%
1/8 (3.25)	14" (350)	.7oz (20g)	22 (49)	21 (46)	95	100%
5/32 (4.0)	14" (350)	1 oz (29g)	15 (33)	18 (40)	120	100%

APPROXIMATE ELECTRODE PACKAGING & DIMENSIONS

Diameter (mm)	1/16 (1.6)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Length (mm)	10" (250)	12" (300)	12" (300)	14" (350)	14" (350)
Electrodes / lb	67	42	28	13	9
Electrodes / kg	147	92	62	29	20