



Manufacturers of Custom Welding Lines for Resale
www.selectrode.com

SELECTRODE 1182

High Deposition 309L Stainless
Steel

INTERNATIONAL CLASSIFICATIONS

AWS/ASME A 5.4 E 309L-26

FEATURES & APPLICATIONS

Wherever maximum ductility is required when joining dissimilar steels to themselves or to stainless steels

Extra strong and tough stainless steel electrode for joining steels to stainless steels

- Highly recommended for joining hard to weld steels
- Moisture resistant coating provides sound porosity free deposits
- Slag is self removing

ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

Microstructure: Austenite with a ferrite number of 8

Flux Color: Blue

C	Mn	Si	Cr	Ni	Fe
0.04	1.8	0.6	23.3	12.2	Bal.

TYPICAL MECHANICAL PROPERTIES

Undiluted Weld Metal

Tensile Strength

Maximum Value Up to:

110,000 PSI (750 MPa)

Yield Strength	76,000 PSI (530 MPa)
Elongation	32%
Impact Energy	50J: 68°F (20°C)
Hardness	Brinell 219, Rockwell C 14

WELDING CURRENT & INSTRUCTIONS

Recommended Current: DC Reverse (+) or AC

Diameter (mm)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Minimum Amperage	50	65	90	145
Maximum Amperage	75	105	145	215

Welding Techniques: Weld with the electrode tilted slightly using a short arc or the drag technique. This high recovery electrode allows you to use smaller than normal electrode diameters.

Welding Positions: Flat, Horizontal, Vertical up

Deposition Rates:

Diameter (mm)	Length (mm)	Weldmetal/ Electrode	Electrodes per lb (kg) of Weldmetal	Arc Time of Deposition min/ lb (kg)	Amperage Settings	Recovery Rate
1/16 (1.6)	10" (250)	.35oz (10g)	46 (102)	36 (79)	65	170%
3/32 (2.5)	14" (350)	.7 oz. (20g)	23 (50)	25 (56)	85	170%
1/8 (3.25)	14"(350)	1.14oz (32g)	14 (30)	17 (38)	120	170%
5/32 (4.0)	14" (350)	1.78 oz (50g)	9 (20)	10 (23)	180	170%

APPROXIMATE ELECTRODE PACKAGING & DIMENSIONS

Diameter (mm)	1/16 (1.6)	5/64 (2.0)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Length (mm)	10" (250)	12" (300)	12" (300)	14" (350)	14" (350)
Electrodes / lb	67	42	28	13	9
Electrodes / kg	147	92	62	29	20