

Manufacturers of Custom Welding Lines for Resale www.selectrode.com



CODE 7260 – Metal I Core - COMBO - WEAR FEATURES & APPLICATIONS

Description: Excellent all position alloy for general hardfacing to resist moderate abrasion combined with impact.

Application: Assorted dies, sliding metal parts, impact drills, etc.

A high technology group of all position metal cored wearfacing tubular wires All components are baked at extra high temperatures before manufacturing to eliminate

moisture pick up

Excellent in all positions

Slag free deposits represent very high transfer efficiency

 Settings:
 .045" (1.2mm) D.C.R.P., 18-30 Volts, 125-250 Amps, 75% Ar-25% CO²

 1/16" (1.6mm) D.C.R.P., 20-30 Volts, 150-300 Amps, 75% Ar-25% CO²

ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

	Mn							
.5	1.02	.55	.01	.02	6.7	.65	.50	Bal

TYPICAL MECHANICAL PROPERTIES

Hardness: Standard Spool Size: RC 57-59 25# (11.36 Kg.)